

## Specification \*

100% TCF (Totally Chlorine Free)

Grammage (g/m <sup>2</sup> ) ISO 536	65	70	75	80	90
Brightness, % ISO 2470 D65	88	90	90	90	90
Opacity, % ISO 2471	92.0	93.5	94.0	95.0	96.0
Gloss, % T480 Hunter 75°	62	62	63	63	63
Bulk, cm <sup>3</sup> /g	0.9	0.9	0.9	0.9	0.9
L*, % ISO 5631 D65 C/2	92	93	93	93	93
a*, % ISO 5631 D65 C/2	0.4	0.4	0.4	0.4	0.4
b*, % ISO 5631 D65 C/2	-4	-5	-5	-5.5	-5.5

\*The values given are target values and variations occur.

### Producer

SCA Ortviken, Sweden

### Areas of applications

Magazines, supplements and inserts printed in heatset web offset.

### Reel diameters

Standard diameters are 100, 120 and 125 cm.  
(Machine width max 6.39 m.)

### Reel width

The minimum reel width which can be produced is 400 mm.

### Web length

Approximately:

g/m <sup>2</sup>	65	70	75	80	90
Ø 100 cm	14500	13500	12500	11500	10500
Ø 120 cm	21000	19500	18000	17000	16000
Ø 125 cm	23000	21000	19500	18000	16500

### Environment

TCF (totally chlorine-free) and certified in accordance with ISO 9001 and 14001. Chain of Custody in accordance with FSC and PEFC.

### Wrapping

Reels are wrapped in polyethene laminated liner with inner endshields of corrugated board and polyethene coated outer endshields.

### Packing

Reels less than 600 mm in width are always co-packed.

### Surface pH value

The surface pH value of the paper is >6.

Rev. 2012-02-16

For further information and samples, please contact

### SCA ORTVIKEN

SCA Graphic Sundsvall AB

Box 846

SE-851 23 SUNDSVALL

[www.publicationpapers.sca.com](http://www.publicationpapers.sca.com)

