

Technical target values

Grammage (g/m ²) ISO 536	51	54	57	60	65	70	80
Brightness % ISO 2470 D65	76	76	78	78	78	78	78
Opacity % ISO 2471	90	91	92	92.5	94	95	96
Gloss, % Hunter ISO 8254-1	43	46	48	50	51	52	52
Bulk, cm³/g ISO 534	1.0	1.0	1.0	1.0	1.0	1.0	1.0
L* ISO 5631 D65	89	89	90	90	91	91	91
a* ISO 5631 D65	-0.3	-0.3	-0.3	-0.3	-0.3	-0.3	-0.3
b* ISO 5631 D65	-0.3	-0.3	-1.0	-1.0	-1.0	-1.0	-1.0

The values given are target values and variations occur.

Producer
SCA Ortviken, Sweden.

Areas of applications
Magazines, supplements and inserts printed in heatset web offset.

Reel diameters
Standard diameters are 100, 120 and 125 cm.

Reel width
Available range is 400 - 2860 mm.

Core
76 and 152 mm.

Web length
Approximately:

g/m ²	51	54	57	60	65	70	80
Ø 100 cm	16000	15 500	15 000	14 000	13 000	12 200	11 000
Ø 120 cm	24000	22 500	21 500	20 500	18 000	17 700	16 000
Ø 125 cm	26500	24 500	23 500	22 000	19 000	19 100	18 000

Environment

The mill is certified in accordance with ISO 9001 and 14001.
Chain of Custody in accordance with FSC and PEFC.

Wrapping

Reels are wrapped in polyethene laminated liner inner end shields of corrugated board and polyethene coated outer end shields.

Packing

Reels less than 600 mm in width are always co-packed and marked with a red stripe.

Surface pH value

The surface pH value of the paper is >6.

For colour profile information, please contact the technical service representative at your local sales office.

Rev. 2018-09-06

For further information and samples, please contact:

SCA ORTVIKEN

SCA Graphic Sundsvall AB
Box 846
SE-851 23 SUNDSVALL
www.sca.com/publicationpapers