



Technical target values

Grammage (g/m ²) ISO 536	60	65	70	75	80	90
Brightness, % ISO 2470 D65	90	90	91	92	92	93
Opacity, % ISO 2471	92	93	94.5	95	96	97
CIE Whiteness ISO 11476 D65	108	108	108	112	112	115
Gloss, % ISO 8254-1	35	35	35	35	35	35
Bulk, cm³/g ISO 534	1.0	1.0	1.0	1.0	1.0	1.0
L* ISO 5631 D65	92	92	93	93	93	93
a* ISO 5631 D65	0.6	0.6	0.6	0.6	0.6	0.8
b* ISO 5631 D65	-5.5	-5.5	-6.0	-6.5	-6.5	-7

The values given are target values and variations occur.

Producer

SCA Ortviken, Sweden

Areas of applications

Magazines, supplements and inserts printed in heatset web offset.

Reel diameters

Standard diameters are 100, 120 and 125 cm.

Reel width

Available range is 400 - 2720 mm.

Core

76 and 152 mm.

Web length

Approximately:

g/m ²	60	65	70	75	80	90
Ø 100 cm	14000	12900	12000	11200	10400	9300
Ø 120 cm	20100	18600	17300	16100	15000	13400
Ø 125 cm	21900	20200	18800	17500	16300	14500

Environment

The mill is certified in accordance with ISO 9001 and 14001.
Chain of Custody in accordance with FSC and PEFC.

Wrapping

Reels are wrapped in polyethylene laminated liner with inner end shields of corrugated board and polyethylene coated outer end shields.

Packing

Reels less than 600 mm in width are always co-packed and marked with a red stripe.

Surface pH value

The surface pH value of the paper is >6.

For colour profile information, please contact the technical service representative at your local sales office.

Rev. 2019-05-14

For further information and samples, please contact:

SCA ORTVIKEN

SCA Graphic Sundsvall AB

Box 846

SE-851 23 SUNDSVALL

www.sca.com/publicationpapers