



Technical target values

Grammage (g/m ²) ISO 536	51	54	57	60	65	70
Brightness, % ISO 2470 D65	87	87	87	87	87	87
Opacity, % ISO 2471	91	92	93	93	94	95
Gloss, % ISO 8254-1	25	25	25	25	25	25
Bulk, cm ³ /g ISO 534	1.3	1.3	1.3	1.3	1.3	1.3
L* ISO 5631 D65	92	92	92	92	92	92
a* ISO 5631 D65	-0.1	-0.1	-0.1	-0.1	-0.1	-0.1
b* ISO 5631 D65	-5	-5	-5	-5	-5	-5

The values given are target values and variations occur.

Producer

SCA Ortviken, Sweden.

Areas of applications

Magazines, supplements and inserts printed in heatset web offset.

Reel diameters

Standard diameters are 100, 120 and 125 cm.

Reel width

Available range is 400 - 2860 mm.

Core

76 and 152 mm.

Web length

Approximately:

g/m ²	51	54	57	60	65	70
Ø 100 cn	12 000	11 500	11 000	10 500	9 500	9 300
Ø 120 cn	17 500	16 500	15 500	15 000	14 000	12 400
Ø 125 cn	19 000	18 000	17 000	16 000	15 000	14 500

Environment

The mill is certified in accordance with ISO 9001 and 14001. Chain of Custody in accordance with FSC and PEFC.

Wrapping

Reels are wrapped in polyethene laminated liner with inner end shields of corrugated board and polyethene coated outer end shields.

Packing

Reels less than 600 mm in width are always co-packed and marked with a red stripe.

Surface pH value

The surface pH value of the paper is >6.

For colour profile information, please contact the technical service representative at your local sales office.

Rev. 2018-09-06

For further information and samples, please contact:

SCA ORTVIKEN

SCA Graphic Sundsvall AB

Box 846

SE-851 23 SUNDSVALL

www.sca.com/publicationpapers