

Technical target values

Grammage (g/m ²) ISO 536	70	80	90	100
Brightness, % ISO 2470 D65	92	93	94	95
Opacity, % ISO 2471	96	97	98	99
CIE Whiteness ISO 11476 D65	112	114	116	117
Gloss, % ISO 8254-1	15	15	15	15
Bulk, cm³/g ISO 534	1.2	1.2	1.2	1.2
L* ISO 5631 D65	93	93	93	93
a* ISO 5631 D65	0.6	0.6	0.8	0.8
b* ISO 5631 D65	-6.0	-6.5	-7	-7

The values given are target values and variations occur.

Producer

SCA Ortviken, Sweden

Areas of applications

Magazines, supplements and inserts printed in heatset web offset.

Reel diameters

Standard diameters are 100, 120 and 125 cm.

Reel width

Available range is 400 - 2720 mm.

Core

76 and 152 mm.

Web length

Approximately:

g/m ²	70	80	90	100
Ø 100 cm	9800	8900	8000	7300
Ø 120 cm	14200	12800	11600	10600
Ø 125 cm	15400	14000	12600	11500

Environment

The mill is certified in accordance with ISO 9001 and 14001. Chain of Custody in accordance with FSC and PEFC.

Wrapping

Reels are wrapped in polyethene laminated liner with inner end shields of corrugated board and polyethene coated outer end shields.

Packing

Reels less than 600 mm in width are always co-packed and marked with a red stripe.

Surface pH value

The surface pH value of the paper is >6.

For colour profile information, please contact the technical service representative at your local sales office.

For further information and samples, please contact:

SCA ORTVIKEN

SCA Graphic Sundsvall AB

Box 846

SE-851 23 SUNDSVALL

www.sca.com/publicationpapers