

## Technical target values

Grammage (g/m <sup>2</sup> ) ISO 536	45	49
Brightness, % ISO 2470 D65	62	62
Opacity, % ISO 2471	94	95
Bulk, cm <sup>3</sup> /g ISO 534	1.6	1,6
L* ISO 5631 D65	85	85
a* ISO 5631 D65	-1.2	-1.2
b* ISO 5631 D65	3.9	3.9

*The values given are target values and variations occur.*

### Producer

SCA Ortviken, Sweden.

### Areas of applications

When a fresh and clean look is preferred. Good contrast and brilliance make this sheet suitable for more demanding four-colour images. High bulk for quality feel and stability in the folder and the mail-room. Unique environmental profile. For printing in heatset and coldset web offset.

### Reel diameters

Standard diameters are 100, 120 and 125 cm.

### Reel width

Available range is 370 - 2860 mm.

### Core

76 and 152 mm.

### Web length

Approximately:

g/m <sup>2</sup>	45	49
Ø 100 cm	11 900	11 100
Ø 120 cm	17 100	15 900
Ø 125 cm	18 600	17 300

### Environment

The mill is certified in accordance with ISO 9001 and 14001. Chain of Custody in accordance with FSC and PEFC.

### Wrapping

Reels are wrapped in polyethene laminated liner with inner end shields of corrugated board and polyethene coated outer end shields.

### Packing

Reels less than 600 mm in width are always co-packed and marked with a red stripe.

### Surface pH value

The pH value of the paper is >6.

**For colour profile information**, please contact the technical service representative at your local sales office.

Rev 2018-09-06

For further information and samples, please contact:

### SCA ORTVIKEN

SCA Graphic Sundsvall AB

Box 846

SE-851 23 SUNDSVALL

[www.sca.com/publicationpapers](http://www.sca.com/publicationpapers)